

FEATURES

Long oil alkyd resin primer with Zinc Phosphate pigment that helps protecting the surface from rust. Recommended for iron and steel surfaces.

- Rust preventive
- Fast-dry & easy to apply
- Good adhesion & hiding power

PRODUCT INFORMATION

| | |
|-----------------------|--|
| Paint type | Long Oil Alkyd Resin |
| Product type | Exterior & Interior |
| Film appearance | Matt |
| Color | Gray |
| Grade | Economy |
| Recommended substrate | Metal i.e. metal construction |
| Pack size | 0.875 Litres, 3.5 Litres and 17.5 Litres |

TECHNICAL INFORMATION

| | | |
|----------------------|---|---------------------------------------|
| Theoretical coverage | 44-52 | m ² per 3.5 Litre per coat |
| Practical coverage | 38-43 | m ² per 3.5 Litre per coat |
| | These values are calculated based on the above theoretical coverage and a loss factor of 20% The actual loss factor for a particular job may vary depending on the application condition, method and technique; surface condition; as well as the structure and dimension of the object to be coated. | |
| No. of coat | 1-2 | coats |
| Solid by volume | 60±2 | % |
| Solid by weight | 76±2 | % |
| VOC | <450 | g/L |
| Wet film thickness | 59-67 | microns |
| Dry film thickness | 35-40 | microns |
| Touch dry (25-30°C) | 40 | mins |
| Recoat dry (25-30°C) | 4 | hrs. |
| Full cure (25-30°C) | 7 | days |

REFERENCE STANDARD

-

APPLICATION

| | |
|--------------|---|
| Applicator | Brush, Roller or Spray |
| Diluted by | Nippon Alkyd thinner or Hi-Thinner #01 |
| Dilution (%) | Dilute the paint up to 5 % when apply by brush or roller, and 10 % when apply by spray. |

SURFACE PREPARATION

| | |
|-------|---|
| Metal | Surface must be dry and free from dirt, grease and other contaminants. Ferrous substrate should be sanded or wire-brushed to remove mill scales and rust. Clean off dust and dry. |
|-------|---|

PAINT SYSTEM

| | |
|--------------------------|---|
| Primer for metal surface | Junior 99 Grey Oxide Primer 1-2 coats |
| Top coat | Junior 99 Enamel 2-3 coats |
| | Note: In case of vivid and intense color shade, a lighter shade is recommended to apply in the first coat for a good hiding result. |

HANDLING AND STORAGE

| | |
|-------------------|--|
| Storage condition | The product must be stored in a dry, well-ventilated space and keep the container tightly closed. When transporting paint, the product should separately from others. Not recommended to place the product outdoor or exposed to the sun directly and must separately be stored between enamel paint and thinner, which is a flammable substance. |
| Precipitation | Place the product for a long time may lead the pigment to precipitate at the bottom of the container and can deteriorate over time when not stir product to a homogeneous by using suitable tools, such as an electric drill, air drill, or a stirrer. Therefore, should stir the product to the homogeneous phase before use. If not, the product will cause paint problems e.g. low hiding power or non-equal color shade. |
| Shelf life | 2 years at 30-35 °C |

SAFETY PRECAUTIONS

Precautionary notices are displayed on the container. Use product under well-ventilated area. Avoiding skin contact or inhale product. In case of contact with the eye, rinse with plenty of water immediately and seek medical advice. Remove splashes from the skin by using soap or water. For others information in terms of health and safety hazards for use of this product, please observe the Safety Data Sheet.

DISCLAIMER

The above information is given to the best of our knowledge based on laboratory tests and practical experience. However, since we cannot anticipate or control the many conditions under which our products may be used, we can only guarantee the quality of the product itself.

We reserve the right to alter the given without prior notice.

NOTE

The data are average values for reference only. However, the actual value depends on environmental conditions.