

# NIPPON PAINT AQUA EPOXY

## **FEATURES**

Nippon Paint Aqua Epoxy is a two-pack epoxy water-based paint that dries due to the reaction of amine-adduct hardener. Suitable for indoor paint e.g. cementitious surface, plastered wall, and also ceramic tile.

- Excellent abrasion and impact resistance
- Washable
- · Low odour and non-added lead or mercury
- · Excellent adhesion on concrete floor
- Can be used with walls and floors that require light to medium loads
- Available on Colour Creation Machines (CCM)

## **PRODUCT INFORMATION**

Paint type Epoxy water-based paint

Product type Interior
Film appearance Gloss

Color Various colors see in color cards

Grade Heavy Duty Coatings

Recommended substrate Concrete, Fibercement and Ceramic tile

Pack size 5 Litres per set

## **TECHNICAL INFORMATION**

Theoretical coverage	10	m <sup>2</sup> per litre per coat (at dry film thickness 50 micron)
	6.3	m <sup>2</sup> per litre per coat (at dry film thickness 80 micron)
Practical coverage	8.0	m <sup>2</sup> per litre per coat (at dry film thickness 50 micron)
	5.0	m <sup>2</sup> per litre per coat (at dry film thickness 80 micron)

These value are calculated based on the above theoretical coverage and a loss factor of 20% The actual loss factor for a particular job may vary depending on the application condition, method and technique; surface condition; as well as the structure and dimension of the object to be coated.

No. of coat 2 coats
Specific gravity 1.10-1.15 (Mixed)

Solid by volume  $50\pm5$  % VOC (EPA Method 24) 40-50 g/L Wet film thickness 100-160 microns Dry film thickness 50-80 microns

Touch dry (25-30°C) Approx.. 4 hrs.

Recoat dry (25-30°C) Approx.. 12 hrs.

Full cure (25-30°C) 7 days

## REFERENCE STANDARD

-

Page 1/3 www.nipponpaintdecor.com



# NIPPON PAINT AQUA EPOXY

**APPILCATION** 

**Applicator** 

Brush, Roller, Spray and Airless spray

Guiding data for airless spray

Tip size 0.015-0.023 inch

Delivery pressure 140-170 Bar

Diluted by Water

Dilution (%) Dilute the paint with 5-10% of water when apply with Airless spray, Brush and Roller.

Mixing ratio (Part A : Part B) 4:1 by volume

Pot life 1 hrs at 25-30 °C

**SURFACE PREPARATION** 

Cement old surfaces Remove all loose, defective paint or powdery residues, loose chalk, dust, fungus, algae and

foreign matter. (avoid wire brush)

Repair cracks, uneven surfaces with Nippon Paint Vinilex Wall Putty.

Treat any areas affected by fungus growth by scrubbing and allowing the surface to dry completely before painting then apply with Nippon Paint Vinilex Bio Wash 1 coat and leave it

until dry.

Cement new surfaces Ensure that the surface is clean and dry it must be free from dirt, greases and other foreign

natters.

Allow all surfaces to dry completely prior to painting. (At least 28 days)

Avoid painting when the moisture content and alkalinity of the walls are still high. (Recommended painting specification requires the moisture content of the walls to be below 14% measured by protimeter, below 6% by Kett model HI-520 and alkalinity of the walls to be below

pH 8.)

Repair cracks, uneven surfaces with Nippon Paint Vinilex Wall Putty.

Other surfaces The surface should be cleaned and free from contamination according to each substrate.

**PAINT SYSTEM** 

Top coat

Primer for cement old surfaces Nippon Paint Aqua Epoxy Primer 1 coat

Primer for cement new surfaces Nippon Paint Aqua Epoxy Primer 1 coat

Primer for ceramic tile Nippon Paint Aqua Epoxy Primer 1 coat

Note: In case of vivid and intense color shade, a lighter shade is recommended to apply in the

first coat for a good hiding result.

Nippon Paint Aqua Epoxy 2 coats

**HANDLING AND STORAGE** 

Storage condition The product must be stored in a dry, well-ventilated space and keep the container tightly closed.

When transporting paint, the product should separately from others. Not recommended to place the product outdoor or exposed to the sun directly and must separately be stored between

enamel paint and thinner, which is a flammable substance.

Precipitation Place the product for a long time may lead the pigment to precipitate at the bottom of the container and can deteriorate over time when not stir product to a homogeneous by using

suitable tools, such as an electric drill, air drill, or a stirrer. Therefore, should stir the product to the homogeneous phase before use. If not, the product will cause paint problems e.g. low hiding

power or non-equal color shade.

Shelf life at 25-30 °C 24 months

www.nipponpaintdecor.com



# **NIPPON PAINT AQUA EPOXY**

ENVIRONMENTAL CONDITION

**SAFETY PRECAUTIONS** 

**DISCLAMER** 

**NOTE** 

The relative humidity during application should not exceed 85% or when the surface to be painted is more than 3°C above the dew point. Generally, the temperature of surface to be painted should be more than 5 °C and not exceed 50°C.

Precautionary notices are displayed on the container. Use product under well-ventilated area. Avoiding skin contact or inhale product. In case of contact with the eye, rinse with plenty of water immediately and seek medical advice. Remove splashes from the skin by using soap or water. For others information in terms of health and safety hazards for use of this product, please observe the Safety Data Sheet.

The above information is given to the best of our knowledge based on laboratory tests and practical experience. However, since we cannot anticipate or control the many conditions under which our products may be used, we can only guarantee the quality of the product itself.

We reserve the right to alter the given without prior notice.

The data are average values for reference only. However, the actual value depends on environmental conditions.

Page 3/3